

tungstenselection



MAXIMIZE ARC STARTING AND IMPROVE ARC TIME
WITH HIGH-QUALITY TUNGSTEN ELECTRODES

from 

Selecting the proper tungsten electrodes will greatly improve weld quality and productivity while lowering costs for your Gas Tungsten Arc Welding (GTAW/TIG) and Plasma Arc Welding (PAW) operations.

1. CHOOSE ELECTRODES FROM A TRUSTED SOURCE.

Although tungsten electrodes may look the same from one company to another, high-quality tungsten has been manufactured to ensure a very small grain structure which allows for better migration of oxides to the tip of the electrode.

With high-quality tungsten, you'll also experience easier arc starting, improved arc time and better weld quality with minimized contamination.

Arc-Zone.com's ArcTime™ and Amplify™ brand electrodes are from the world's finest producers and meet or exceed ISO 6848 and AWS A5.12 standards. Arc-Zone.com® delivers the industry's most complete line of premier tungsten electrodes including ArcTime™, Amplify™, Multi-Strike™, SYLVANIA, and Weldcraft®.



2. DETERMINE THE BEST TUNGSTEN/TUNGSTEN ALLOY FOR YOUR APPLICATION

Since the development of the TIG welding process, many improvements have been made in the production of electrodes. Most significantly is the addition of oxides to pure tungsten, creating tungsten alloys that provide the same level of emission as pure tungsten at much lower temperatures, improving the arc time of the electrode, and improving arc stability.

Each oxide has a different physical characteristic affecting tungsten performance. Electrodes are color coded, indicating the type of oxide used in the mix. Note that color-coding is not standardized for all mixes and varies from the U.S. to Europe and Japan.

For most hand-held welding operations, Arc-Zone® recommends the ArcTime™ Hybrid Tungsten Electrode. For other applications, particularly automated welding, the best way to determine which tungsten alloy is best suited for your application is through testing. The following list is provided as a guide.



Copyright©2008, Arc-Zone.com®, Inc. All Rights Reserved

Arc-Zone.com, Inc.
2091 Las Palmas Drive, Ste. F
Carlsbad, CA 92011-1551
Tel. 1.760.931.1500/1.800.944.2243
Fax. 1.760.931.1504 Email: info@arc-zone.com

▶ **ArcTime™ ..Hybrid All Purpose Tungsten Electrodes**

This non-radioactive state-of-the-art formula combines rare earth materials with tungsten to produce the best all-purpose tungsten electrode on the market. Experience reliable arc starting even after numerous ignitions.
Color Code: Sky Blue™ (US) Not standardized.



▶ **1% Thoriated...Available in SYLVANIA Brand**

SYLVANIA offers this radioactive tungsten formula for easy arc starting, good arc stability and current capacity, and resistance to weld pool contamination. Not commonly used. Vapors, grinding dust and disposal of thorium dioxide raise health, safety and environmental concerns. Use only when contractually required by FAR specification.
Color Code: Yellow



▶ **2% Thoriated...Available in Amplify™, SYLVANIA, and Weldcraft® Brands**

This formula is a popular general purpose electrode due to the excellent arc behavior and good tip life. This is a radioactive formula, however. Vapors, grinding dust and disposal of thorium dioxide raise health, safety and environmental concerns. Use only when contractually required by FAR specification.
Color Code: Red (US, Europe and Japan)



▶ **2% Lanthanated...Available in Amplify™ Brand**

This formula is a good general purpose non-radioactive replacement for 2% Thoriated. It has excellent ignition performance, low-burn-off rate, excellent re-ignition, and good service life.
Color Code: Blue (US) Not standardized in Europe. Yellow-Green (Japan)



▶ **1.5% Lanthanated...Available in Amplify™, SYLVANIA, and Weldcraft® Brands**

Another good general-purpose non-radioactive replacement for 2% Thoriated, and similar in performance to 2% lanthanated. It features excellent ignition and re-ignition properties and good service life.
Color Code: Gold (US) Not standardized in Europe or Japan.



▶ **2% Ceriated...Available in Amplify™, SYLVANIA, and Weldcraft® Brands**

Good for low-amp, DC orbital tube, pipe, thin sheet, and small part applications, this formula offers low current capacity, low arc ignition, good arc stability and is non-radioactive.
Color Code: Orange (US) Gray (Europe and Japan)



▶ **1% Zirconiated...Available in Amplify™ and SYLVANIA Brands**

Used for radiographic-quality welding where tungsten contamination must be minimized. Balls-up easily in AC applications, good arc starting and current capacity. Non-Radioactive.
Color Code: Brown (US) White (Europe) Not standardized in Japan.



▶ **Pure Tungsten...Available in Amplify™, SYLVANIA, and Weldcraft® Brands**

Pure tungsten has a high work-function which makes it difficult to start and maintain a stable arc. High burn-off rate results in short service life.
Color Code: Green (US, Europe and Japan)



Other tungsten blends that are not common but you may see in the market place include: 4% Thoriated, 3% Thoriated, and 1% Lanthanated. Color codes are not standardized in the U.S. Again, purchasing from a trusted source is important as manufacturing methods can greatly affect tungsten electrode performance.

3. SELECT THE PROPER SIZE

Tungsten is generally sold in packages of 10 pieces in a variety of standard diameters from .020" (.5mm) to .250" (6.4mm), and in lengths of 3, 6, 7, 12, 18 and 24 inches. The most common length is 7.00" (175mm) in the U.S. and 6.00" (152mm) in Europe. The most common diameters are: .040" (1.0mm), 1/16" (1.6mm), 3/32" (2.4mm), 1/8" (3.2mm), 5/32" (4.0mm), and 3/16" (4.8mm).

Electrode diameter affects welding performance and weld bead shape. Again, the best way to determine which tungsten is best suited for your application is through testing, however, the following chart should serve as a general guide.

TUNGSTEN ELECTRODES RATING FOR WELDING CURRENTS

Electrode Diameter	Direct Current		Alternating Current	
	Straight Polarity	Reverse Polarity	Unbalanced Wave	Balanced Wave
	DCEN	DCEP		
.020" (0.50 mm)	5-2	n/a	5-15	10-20
.040" (1.0 mm)	15-80	n/a	10-60	20-30
1/16" (1.6 mm)	70-150	10-20	50-100	30-80
3/32" (2.4 mm)	150-250	15-30	100-160	60-130
1/8" (3.2 mm)	250-400	25-40	150-210	100-180
5/32" (4.0 mm)	400-500	40-55	200-275	160-240
3/16" (4.8 mm)	500-750	55-80	250-350	190-300
1/4" (6.4 mm)	750-1100	80-125	325-450	325-450

Different electrode materials will vary slightly from these guidelines. Use of other gases will also change the recommended currents. Use this chart as a general guide. Also keep in mind that for a given amount of amperage, larger diameter electrodes will last longer but will be harder to start. Excessive current will cause the electrode to melt and drop off. Insufficient current will lead to an unstable arc.

For further assistance in selecting the correct tungsten electrode for your welding application, please contact an Arc-Zone.com® technician via email at info@arc-zone.com, phone toll free **800-944-2243** or call worldwide: **760-931-1500**.



Copyright©2008, Arc-Zone.com®, Inc. All Rights Reserved

Arc-Zone.com, Inc.
 2091 Las Palmas Drive, Ste. F
 Carlsbad, CA 92011-1551
 Tel. 1.760.931.1500/1.800.944.2243
 Fax. 1.760.931.1504 Email: info@arc-zone.com

tungstengrinders



TUNGSTEN GRINDER SELECTOR GUIDE



Tungsten Grinder	Cost	Style	Grind Angles	Degree Scale for Taper	Tip Flat Capable	Cut-Off Capable	Dust Collection	Tungsten Diameters
Sharpie Standard Tungsten Grinder	\$229	Hand-Held	20° Fixed	fixed grinding position	✓	✓		.040"-1/8" (1.0mm-3.2mm)
Sharpie Deluxe Tungsten Grinder	\$279	Hand-Held	5° - 45°		✓	✓		.040"-1/8" (1.0mm-3.2mm)
Sharpie DXV Vacuum Tungsten Grinder	\$379	Hand-Held	5° - 45°		✓	✓	vacuum	.040"-1/8" (1.0mm-3.2mm)
Turbosharp V	\$635	Hand-Held w/ Bench Mounting Bracket	20° - 60°	✓	✓		fully enclosed	.040"-3/16" (1.0mm-4.8mm)
Triad	\$835	Hand-Held w/ Bench Mounting Bracket	15°, 18°, 22.5°, 30°	fixed grinding positions	✓	✓		.040"-5/32" (1.0mm-4.0mm)
Neutrix	\$990	Hand-Held w/ Bench Mounting Bracket	15° -90°	✓	✓		fully enclosed	.040"-5/32" (1.0mm-4.0mm)
Turbo 4	\$795	Semi-Portable Bench-Top	5° - 60°	✓		✓	semi-enclosed	.040"-5/32" (1.0mm-4.0mm)
Piranha 2	\$875	Semi-Portable Bench-Top	10° - 60°	✓	✓	✓		.040"-3/32" (1.0mm-2.4mm)
TEG-3	\$1,550	Semi-Portable Bench-Top	15° - 90°	✓	✓		semi-enclosed	1/16"-5/32" (1.0mm-4.0mm)
Piranha 3	\$1,562	Bench-Top	10° - 60°	✓	✓	✓		.040"-3/16" (1.0mm-4.8mm)
Neutra LTG	\$1,560	Bench Mounted	10° - 50°	✓	✓		fully enclosed	.040"-3/16" (1.0mm-4.8mm)
Ultima LTG (EU Model Only)	\$1,621	Bench Mounted	10° - 50°	✓	✓		fully enclosed	.040"-3/16" (1.0mm-4.8mm)
TIG 10/175	\$2,305	Bench Mounted w/ optional grinding station	0° - 90°	✓	✓ +	✓	optional vacuum	.040"-3/16" (1.0mm-4.8mm)
DGP-3-V2	\$3,356	Complete Grinding Station	6° - 120°	✓	✓	✓ +	vacuum	.040"-3/16" (1.0mm-4.8mm)
Sharp Shooter	\$3,995	Complete Grinding Station	10° - 60°	✓	✓	✓ +	fully enclosed w/ vacuum	.040"-3/16" (1.0mm-4.8mm)

✓ + Tip Flat = Micrometer Tip Flat Gauge

✓ + Cut Off = Micrometer Cut Off Gauge



Copyright©2008, Arc-Zone.com®, Inc. All Rights Reserved

Arc-Zone.com, Inc.
 2091 Las Palmas Drive, Ste. F
 Carlsbad, CA 92011-1551
 Tel. 1.760.931.1500/1.800.944.2243
 Fax. 1.760.931.1504 Email: info@arc-zone.com